



Martini dECO VELOUR

Velcro® receptive acoustic fabric

A large, light blue, stylized lowercase 'm' graphic that spans the bottom half of the page.

CSR



Our dECO Velour range offers bold modern colours with a palette of neutrals. The soft, plush feel of dECO Velour adds an opulent surface texture to any interior. It's inherently durable, does not fray and is Velcro® receptive, offering unlimited styling possibilities.



Martini dECO Velour

Physical Description and Properties

Melting point:	250°C
Flash point:	None allocated
Other properties:	Non-allergenic, low irritant, low flame response, resilient
Ingredients:	Organic, long chain synthetic polymer
Max service temp:	110°C
Alkalinity:	pH 7.8 (pH 7 is neutral)
Moisture absorption:	Exposure to an atmosphere of 50°C and 95% RH for four days gives moisture absorption of less than 0.2% by volume
Fire resistance:	<div> Tested to AS ISO 9705 Corner Burn in accordance with AS 5637.1 </div> <div> Variations up to XXHD 50mm Group 1-S SMOGRA not more than 100m²/s² x 1000 </div>
Luminous reflectance:	As per ASTM E1477-98A: 2017

Apple	30.1	Moss	11.9
Ariel	47.50	Neptune	44.19
Ash	20.38	Nordic Sky	56.74
Bolt	43.48	Pitch	1.9
Bumble Bee	74.69	Platinum	12.0
Candy	33.47	Porcelain	75.78
Cherry	37.29	Sapphire	3.5
Citrus	19.7	Shamrock	53.34
Granite	53.35	Snow	81.76
Ice	45.7	Summit	17.4
Lace	74.78	Tiger	52.66

Proudly distributed by

HIMMELTM
INTERIOR SYSTEMS

csrmartini.com.au

CSR Martini Pty Limited
P.O. Box 560, Ingleburn NSW 1890
martinienquiries@csr.com.au
1300 767 776

09/22



Disclaimer: The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Martini. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification, please refer to the CSR Martini website for the latest version of this document. The purchaser should independently determine the suitability of the product for the intended use and application.